

Kormax 6061 Aluminium

Material Data Sheet

Aluminium Alloy 6061 is a medium to high strength heat-treatable alloy. It has excellent corrosion resistance to atmospheric conditions, and excellent weldability, although reduced power in the weld zone. It has medium fatigue strength and is widely available.

Chemical Composition (%)

Element		
Aluminium	Al	Balance
Magnesium	Mg	0.8-1.2
Silicon	Si	0.4-0.8
Copper	Cu	0.15-0.4
Chromium	Cr	0.04-0.35
Iron	Fe	0.70 max
Zinc	Zn	0.25 max
Manganese	Mn	0.15 max
Titanium	Ti	0.15 max

Mechanical Properties

	Metric Values	Imperial Values
Tensile Strength Min	310 N/mm ²	45,000 psi
Yield Strength Min	276 N/mm ²	40,000 psi
Elongation Min	10%	10%
Hardness Min	95 BHN	95 BHN
Specific Gravity	2.7 g/cm ³	

The technical data given in this sheet corresponds to our current state of knowledge and should not be construed as an agreement or guarantee regarding certain properties of our products. The decision on the suitability of a particular material for a specific application is up to the user. We reserve the right to modify the given data. Errors of the given data are reserved. The document was produced by machine and is valid without signature.